



广州孚润 400-992-6811

Product Data

## Brayco Micronic 815 Z

Wide Temperature Range

### Description

Castrol Brayco 815Z is a clear water white perfluorinated polyether based fluid. It is virtually inert, compatible with rocket propellants and oxidizers, is unaffected by ultraviolet, cosmic radiation, or high vacuums. It has an exceptionally high viscosity index and low volatility, and has little tendency to form deposits. This product is highly recommended for use in applications at low temperature extremes and in high vacuum. It exhibits excellent lubricating properties, good dielectric properties, excellent shear stability, and low toxicity. Castrol Fluoroclean™ X100 or Castrol Fluoroclean™ HE can be used to remove this lubricant. Refer to the data sheets for information regarding these products.

### Application

Brayco 815Z is essentially insoluble in current fuels and oxidizers, as well as in most organic solvents. This product is intended for use in extreme environments, and has been used successfully in many space missions and in sensitive electronic equipment. It is particularly suited for those applications where extreme vacuums and wide temperature variations are common. Perfluorinated fluids, in general, exhibit excellent shelf lives due to their intrinsic inertness.

## Characteristics

TEST METHOD	DESCRIPTION	RESULT
D 287	Specific Gravity @ 16/16°C (60/60°F)	1.8531
	Pounds per Gallon @ 16°C (60°F)	15.43
D 445	Kinematic Viscosity, cSt	
	@ 99°C (210°F)	45
	@ 38°C (100°F)	148
	@ -40°C (-40°F)	6,500
	@ -54°C (-65°F)	10,855
D 2270	Viscosity Index	350
D 97	Pour Point, °C (°F)	-72 (-100)
BOC	Evaporation Loss, % wt	
	72 hrs, 232°C (450°F)	0.36
D 664	Acid Number, mgKOH/g (end point, pH=8.2)	0.01
Knudsen	Vapor Pressure, torr	
	@ 20°C (68°F)	$4 \times 10^{-13}$
	@ 100°C (212°F)	$2 \times 10^{-9}$
E 595	Vacuum Stability Test	
NASA	Total Weight Loss, % wt	0.081
SP-R-0022A	Volatile Condensable Material, % wt	0.012
FTM 3009	Solid Particle Contamination	
	Number of Particles per 100 mL	
	5 - 15 microns	163
	16 - 25 microns	42
	26 - 50 microns	16
	51 - 100 microns	4
	+ 100 microns	Nil

## Additional Information

Temperature Range -72°C to above 204°C (-100°F to 400°F) under normal operating conditions and up to 260°C (500°F) for brief periods. Limitations Brayco 815Z is compatible with all commonly utilized materials, plastics, and elastomers. It may be adversely affected by Lewis Acid Catalysts such as aluminum chloride at elevated temperatures. Newly exposed rubbing surfaces of aluminum, magnesium, or titanium alloys may react with this product under certain conditions. Such systems should be thoroughly evaluated. Surfaces must be well cleaned of organic rust inhibitors prior to oil application to ensure proper lubrication. Packaging Brayco 815Z is packaged in 2 ounce (AVDP) bottles and in 1 pound jars.

Brayco Micronic 815 Z

01 Sep 2016

Castrol, the Castrol logo and related marks are trademarks of Castrol Limited, used under licence.

This data sheet and the information it contains is believed to be accurate as of the date of printing. However, no warranty or representation, express or implied, is made as to its accuracy or completeness. Data provided is based on standard tests under laboratory conditions and is given as a guide only. Users are advised to ensure that they refer to the latest version of this data sheet. It is the responsibility of the user to evaluate and use products safely, to assess suitability for the intended application and to comply with all applicable laws and regulations. Material Safety Data Sheets are available for all our products and should be consulted for appropriate information regarding storage, safe handling, and disposal of the product. No responsibility is taken by either BP plc or its subsidiaries for any damage or injury resulting from abnormal use of the material, from any failure to adhere to recommendations, or from hazards inherent in the nature of the material. All products, services and information supplied are provided under our standard conditions of sale. You should consult our local representative if you require any further information.

Castrol (UK) Limited, PO BOX 352, Chertsey Road, Sunbury On Thames, Middlesex, TW16 9AW

Orders/Enquiries: 0345 9645111 Technical Enquiries: 0345 082 1719

[www.castrol.com/industrial](http://www.castrol.com/industrial)