

Klübersynth BEM 34-32

广州孚润 400-992-6811

Synthetic smooth-running grease for linear guides and bearings in clean room production areas



Benefits for your application

- enables low starting and running torque
- high pressure absorption capacity
- good wear protection
- excellent oxidation and ageing stability
- good water and media resistance

Description

Klübersynth BEM 34-32 is a special high pressure, synthetic, smooth-running grease for use across a wide service temperature range. Its excellent ageing stability allows extended relubrication intervals or lifetime lubrication to be accomplished.

Application

The low base oil viscosity of Klübersynth BEM 34-32 ensures smooth running of linear guides, ball bushings, ball screws, rolling bearings, plain bearings as well as small gear systems in all sectors which are not subject to high vacuum, high temperatures or aggressive media. Due to the excellent metal adhesion properties, Klübersynth BEM 34-32 achieves considerably lower wear rates than many PFPE-based greases used under similar application conditions. The product is compatible with most plastic seals and cage materials.

Application notes

Klübersynth BEM 34-32 can be applied by brush, spatula or preferably by grease gun. Owing to the many different plastic compositions the lubricant's compatibility should be checked prior to series production. Please note that Klübersynth BEM 34-32 takes on a beige-greenish colour under the effects of UV. This does not affect the performance of the lubricating grease.

Material safety data sheets

Material safety data sheets can be requested via our website www.klueber.com. You may also obtain them through your contact person at Klüber Lubrication.

Pack sizes	Klübersynth BEM 34-32
Tube 50 g	+
60 g bellow-type cartridge	+
Cartridge 400 g	+

Product data	Klübersynth BEM 34-32
Article number	004127
Chemical composition, thickener	special calcium soap
Chemical composition, type of oil	synthetic hydrocarbon oil
Lower service temperature	-50 °C / -58 °F
Upper service temperature	130 °C / 266 °F
Colour space	beige
Texture	short-fibred
Texture	homogeneous
Worked penetration, DIN ISO 2137, 25 °C, lower limit value	265 x 0.1 mm



Klübersynth BEM 34-32

广州孚润 400-992-6811

Synthetic smooth-running grease for linear guides and bearings in clean room production areas

Product data	Klübersynth BEM 34-32
Worked penetration, DIN ISO 2137, 25 °C, upper limit value	295 x 0.1 mm
Kinematic viscosity of the base oil, DIN 51562 pt. 01/ASTM D-445/ASTM D 7042, 40 °C	approx. 31 mm ² /s
Kinematic viscosity of the base oil, DIN 51562 pt. 01/ASTM D-445/ASTM D 7042, 100 °C	approx. 5.9 mm ² /s
NLGI grade, DIN 51818	2
Speed factor (n x dm)	approx. 1 000 000 mm/min
Shear viscosity at 25 °C, shear rate 300 s ⁻¹ , equipment: rotational viscometer, lower limit value	2 800 mPas
Shear viscosity at 25°C, shear rate 300 s ⁻¹ , equipment:rotational viscometer, upper limit value	5 200 mPas
Corrosion inhibiting properties of lubricating greases, DIN 51802, (SKF-EMCOR), test duration: 1 week, distilled water	<= 1 corrosion degree
Drop point, DIN ISO 2176, IP 396	>= 220 °C
Water resistance, DIN 51807 pt. 01, 3 h/90 °C, rating	1 - 90
Minimum shelf life from the date of manufacture - in a dry, frost-free place and in the unopened original container, approx.	36 months

Klüber Lubrication – your global specialist

Innovative tribological solutions are our passion. Through personal contact and consultation, we help our customers to be successful worldwide, in all industries and markets. With our ambitious technical concepts and experienced, competent staff we have been fulfilling increasingly demanding requirements by manufacturing efficient high-performance lubricants for more than 80 years.

Klüber Lubrication München SE & Co. KG /
Geisenhausenerstraße 7 / 81379 München / Germany /
phone +49 89 7876-0 / fax +49 89 7876-333.

The data in this document is based on our general experience and knowledge at the time of publication and is intended to give information of possible applications to a reader with technical experience. It constitutes neither an assurance of product properties nor does it release the user from the obligation of performing preliminary field tests with the product selected for a specific application. All data are guide values which depend on the lubricant's composition, the intended use and the application method. The technical values of lubricants change depending on the mechanical, dynamical, chemical and thermal loads, time and pressure. These changes may affect the function of a component. We recommend contacting us to discuss your specific application. If possible we will be pleased to provide a sample for testing on request. Klüber products are continually improved. Therefore, Klüber Lubrication reserves the right to change all the technical data in this document at any time without notice.

Publisher and Copyright: Klüber Lubrication München SE & Co. KG. Reprints, total or in part, are permitted only prior consultation with Klüber Lubrication München SE & Co. KG and if source is indicated and voucher copy is forwarded.