

Klüberquiet BQ 74-73 N

广州孚润 400-992-6811

Low-noise rolling bearing grease for the long-term lubrication of high-speed rolling bearings



Benefits for your application

- Lifetime lubrication of vertically mounted bearings subject to high speeds and/or with a rotating outer ring
- Low-noise spindle bearing grease, also for motor spindles

Description

Klüberquiet BQ 74-73 N is a rolling bearing grease based on synthetic hydrocarbon, ester oil and urea. It was especially developed for the lubrication of high-speed ball bearings operating at high temperatures. With its unique combination of carefully selected raw materials, Klüberquiet BQ 74-73 N offers

- low-noise operation proved in tests on noise test rigs such as SKF BeQuiet
- long bearing life
- wide service temperature range with excellent low-temperature characteristics

Application

Klüberquiet BQ 74-73 N was developed for applications requiring low-noise operation and long service lives, e.g. ball bearings in electric motors, fans, air conditioners, generators and belt tighteners in cars, spindle bearings as well as motor spindles in machine tools, electric as well as other household appliances and office equipment. Because of its consistency, Klüberquiet BQ 74-73 N can be used for rolling bearings that are mounted vertically or have a rotating outer ring.

Material safety data sheets

Material safety data sheets can be requested via our website www.klueber.com. You may also obtain them through your contact person at Klüber Lubrication.

| Pack sizes | Klüberquiet BQ 74-73 N |
|--------------|------------------------|
| Can 1 kg | + |
| Bucket 25 kg | + |

| Product data | Klüberquiet BQ 74-73 N |
|---|--------------------------------|
| Article number | 094098 |
| Chemical composition, thickener | polyurea |
| Chemical composition, type of oil | ester oil |
| Chemical composition, type of oil | synthetic hydrocarbon oil |
| Lower service temperature | -40 °C / -40 °F |
| Upper service temperature | 160 °C / 320 °F |
| Colour space | beige |
| Worked penetration, DIN ISO 2137, 25 °C, lower limit value | 220 x 0.1 mm |
| Worked penetration, DIN ISO 2137, 25 °C, upper limit value | 250 x 0.1 mm |
| Kinematic viscosity of the base oil, DIN 51562 pt. 01/ASTM D-445/ASTM D 7042, 40 °C | approx. 60 mm ² /s |
| Kinematic viscosity of the base oil, DIN 51562 pt. 01/ASTM D-445/ASTM D 7042, 100 °C | approx. 9.5 mm ² /s |
| Corrosion inhibiting properties of lubricating greases, based on DIN 51802, SKF-EMCOR, test duration: 1 week, 5 % NaCl solution | <= 3 corrosion degree |
| Speed factor (n x dm) | approx. 2 000 000 mm/min |
| Copper corrosion, DIN 51811, (lubricating grease), 24h/100°C | 1 - 100 corrosion degree |



Klüberquiet BQ 74-73 N

广州孚润 400-992-6811

Low-noise rolling bearing grease for the long-term lubrication of high-speed rolling bearings

| Product data | Klüberquiet BQ 74-73 N |
|---|------------------------|
| Corrosion inhibiting properties of lubricating greases, DIN 51802, (SKF-EMCOR), test duration: 1 week, distilled water | <= 1 corrosion degree |
| Drop point, DIN ISO 2176, IP 396 | >= 250 °C |
| SKF-ROF rolling bearing tester, axial load: 100 N, radial load: 50 N, speed: 10000 min-1, temperature: 160 °C, service life F50 | >= 1 500 h |
| Low-temperature torque, IP 186, -40 °C, running | <= 100 mNm |
| Low-temperature torque, IP 186, -40 °C, start | <= 1 000 mNm |
| Water resistance, DIN 51807 pt. 01, 3 h/90 °C, rating | <= 1 - 90 |
| Minimum shelf life from the date of manufacture - in a dry, frost-free place and in the unopened original container, approx. | 36 months |

Klüber Lubrication – your global specialist

Innovative tribological solutions are our passion. Through personal contact and consultation, we help our customers to be successful worldwide, in all industries and markets. With our ambitious technical concepts and experienced, competent staff we have been fulfilling increasingly demanding requirements by manufacturing efficient high-performance lubricants for more than 80 years.

**Klüber Lubrication München SE & Co. KG /
Geisenhausenerstraße 7 / 81379 München / Germany /
phone +49 89 7876-0 / fax +49 89 7876-333.**

The data in this document is based on our general experience and knowledge at the time of publication and is intended to give information of possible applications to a reader with technical experience. It constitutes neither an assurance of product properties nor does it release the user from the obligation of performing preliminary field tests with the product selected for a specific application. All data are guide values which depend on the lubricant's composition, the intended use and the application method. The technical values of lubricants change depending on the mechanical, dynamical, chemical and thermal loads, time and pressure. These changes may affect the function of a component. We recommend contacting us to discuss your specific application. If possible we will be pleased to provide a sample for testing on request. Klüber products are continually improved. Therefore, Klüber Lubrication reserves the right to change all the technical data in this document at any time without notice.

Publisher and Copyright: Klüber Lubrication München SE & Co. KG. Reprints, total or in part, are permitted only prior consultation with Klüber Lubrication München SE & Co. KG and if source is indicated and voucher copy is forwarded.