

PRODUCTION COMPOUND

BESTOLIFE® 2000®

广州孚润 400-992-6811

5 Gallon Plastic Pail

PRODUCT CHARACTERISTICS

| | |
|--|---|
| Color: | Dark Copper |
| Penetration: (ASTM D217) | 310 - 330 |
| NLGI Grade: | 1 |
| Weight/Gallon: | 10.4 pounds/gallon |
| Thickener: | Lithium |
| Fluid Type: | Petroleum |
| Particle Size: | <450 microns |
| Dropping Point: (ASTM D2265) | ≥350°F (≥177°C) |
| Flash Point: | ≥392°F (≥200°C) |
| Brushable To: | 10°F (-12°C) |
| Service Rating: | 500°F (260°C) |
| Friction Factor: | .9* |
| Salt Spray Test: (ASTM B117) | 1,250 hours |
| Shelf Life: (Unopened container) | 4 years |
| Contains: | Inert nonmetallic solids and <4% copper flake |

*The proper field torque for all API casing and tubing connections should be determined by following the procedures outlined in API RP 5C1: "Recommended Practice for Care and Use of Casing and Tubing."

A safety data sheet is available from the manufacturer. Do not use on oxygen lines or in oxygen enriched atmospheres.

Note: All package sizes are not listed. Call your sales representative for a complete listing.

DESCRIPTION

BESTOLIFE® 2000® is a lead-free, zinc-free thread compound for casing, tubing, and line pipe. It is stable in high-pressure and high-temperature conditions. An excellent running compound, 2000® also provides superior protection for long-term storage.

APPLICATIONS

Premium lead-free API alternative for casing, tubing, and line pipe; contains no lead or zinc. Formulated for use in high temp steam injection service.

TECHNICAL DATA

BESTOLIFE® 2000® will meet or exceed the listed performance objectives in API RP 5A3. The major solid components are a proprietary blend of nonmetallic materials that are inert to chemical attack, such as occurs in sour gas environments and with CO2 injection. BESTOLIFE® 2000® also addresses one of the major concerns in pipe yards and threading operations today: rejects due to pitting and corrosion. In a salt fog spray test, 2000® demonstrated corrosion protection that exceeds the performance of the leading storage compound in the industry. BESTOLIFE® 2000® conforms to API RP 5A3 evaporation, gas evolution, oil separation, water leaching, copper corrosion and cold application at 19.4°F (-7°C) requirements.

PACKAGING

| PRODUCT NUMBER | CONTAINER SIZE | CONTAINER WEIGHT |
|----------------|----------------|-------------------|
| 615009 | 1 gallon | 9 pounds plastic |
| 615018 | 2 gallon | 18 pounds plastic |
| 615030 | 3 1/2 gallon | 30 pounds plastic |
| 615045 | 5 gallon | 45 pounds plastic |

