

A soft, silica thickened, light synthetic polyglycol grease intended for lubrication of electric contacts exposed to arcing conditions. Base fluid tends to break down to volatiles under arcing rather than to polymerize to gum or to deposit carbon.

Lubricant Properties		Typical Value	Test Method
Recommended Service Range (°C)		-40 to 100	
Thickener		Silica	
Base Oil	Type	Polyglycol	
	Kinematic Viscosity	100°C 40°C -40°C	7 cSt 33.29 cSt 37730 cSt
	Viscosity Index		173
	Flash Point	°C	252
	Pour Point	°C	-57
			ASTM D-445
			ASTM D-2270
			ASTM D-92
			ASTM D-97
Typical Properties of the Grease		Typical Value	Test Method
Color, Appearance		Green, Smooth	
Penetration (1/10 mm)	NLGI Grade	1	ASTM D-217
	Unworked	296	
	Worked	60X 10,000X	323 285
Density		25°C	1.02 g/cm ³
Oil Separation	24 hour(s)	100°C	3.3
Evaporation	24 hour(s)	100°C	0.36
			ASTM D-1480
			ASTM D-6184
			NYE CTM

The typical properties shown on this product data sheet should not be used as a basis for preparing specifications. Refer to our product SDS for detailed safety information on this product. (1504)