UNIFLOR 8170U



广州孚润 400-992-6811

UV Tracer

A medium viscosity, completely fluorinated oil possessing very wide temperature capability, excellent oxidation resistance, excellent plastic and elastomer compatibility and resistance to aggressive chemicals.

	Lubricant Properties		Typical Value	Test Method
Recommended Service Range (°C)			-45 to 225	
Color, Appearance			transparent	
Base Oil	Туре		Perfluoropolyether	
	Kinematic Viscosity	100°C	18 cSt	ASTM D-445
		40°C	162 cSt	
	Viscosity Index		123	ASTM D-2270
	Flash Point	°C	None, Non-Flammable	ASTM D-92
	Pour Point	°C	-48	ASTM D-97
Evaporation	24 hour(s)	150°C	0.26	NYE CTM
Density		25°C	1.89 g/cm3	NYE CTM

The typical properties shown on this product data sheet should not be used as a basis for preparing specifications. Refer to our product SDS for detailed safety information on this product. (1504)