

Electrically Conductive, Rust Inhibited

A carbon black thickened, light viscosity, synthetic hydrocarbon grease intended for electrically conductive, instrument and bearing applications.

Lubricant Properties			Typical Value	Test Method
Recommended Service Range (°C)			-40 to 125	
Thickener			Carbon	
Base Oil			Polyalphaolefin	
(Synthetic Oil 181)	Kinematic Viscosity	40°C	60.7 cSt	ASTM D-445
		100°C	9.5 cSt	
	Viscosity Index		138	ASTM D-2270
	Flash Point		°C 267	ASTM D-92
	Pour Point		°C -57	ASTM D-97
	Typical Properties of the Grease			Typical Value
Color, Appearance			Black, Smooth	
Penetration (1/10 mm)	Unworked		279	ASTM D-217
	Worked		286	
	NLGI Grade		2	
Density		25°C	0.88 g/cm ³	NYE CTM
Oil Separation	24 hour(s)	100°C	1.7	ASTM D-6184
Evaporation	24 hour(s)	100°C	0.1	NYE CTM

The typical properties shown on this product data sheet should not be used as a basis for preparing specifications. Refer to our product SDS for detailed safety information on this product. (1508)