
PG-44A





Rust Inhibited

An extremely stiff, silica soap thickened, heavy viscosity, synthetic hydrocarbon grease intended for applications requiring a very high degree of mechanical damping

	Lubricant Properties		Typical Value	Test Method
Recommended Service Range (°C)			20 to 120	
Thickener			Silica	
Base Oil	Туре		Polybutene	
	Kinematic Viscosity	100°C	4180 cSt	ASTM D-445
		40°C	192000 cSt	
	Viscosity Index		122	ASTM D-2270
	Flash Point	°C	284	ASTM D-92
	Pour Point	°C	28	ASTM D-97
	Typical Properties of	the	Typical Value	Test Method
	Grease			
Color, Appearance			Tan, Tacky	
Penetration	NLGI Grade		5	ASTM D-217
(1/10 mm)	Unworked		146	ASTM D-217
Density		20°C	0.84 g/cm ³	NYE CTM
Oil Separation	24 hour(s)	100°C	0	FTM 791,
				Method 321.2
Evaporation	24 hour(s)	100°C	0.16	

The typical properties shown on this product data sheet should not be used as a basis for preparing specifications. Refer to our product SDS for detailed safety information on this product. (1601)