

## Rust Inhibited

A medium viscosity, completely fluorinated oil possessing very wide temperature capability, excellent oxidation resistance, excellent plastic and elastomer compatibility and resistance to aggressive chemicals.

Lubricant Properties		Typical Value	Test Method	
<b>Recommended Service Range (°C)</b>		-45 to 225		
<b>Color, Appearance</b>		Clear		
<b>Base Oil</b>	Type	Perfluoropolyether		
	Kinematic Viscosity	100°C	18 cSt	ASTM D-445
		40°C	167 cSt	
	Viscosity Index		120	ASTM D-2270
	Flash Point	°C	None, Non-Flammable	ASTM D-92
	Pour Point	°C	-48	ASTM D-97
<b>Evaporation</b>	24 hour(s)	150°C	0.15 %	ASTM D-972
<b>Density</b>		25°C	1.89 g/cm <sup>3</sup>	NYE CTM

The typical properties shown on this product data sheet should not be used as a basis for preparing specifications. Refer to our product SDS for detailed safety information on this product. (1504)