

## Rust Inhibited, Tackifier, EP Fortified

A lithium soap thickened, medium viscosity, synthetic hydrocarbon grease intended for highly loaded gear applications.

Lubricant Properties		Typical Value	Test Method
<b>Recommended Service Range (°C)</b>		-20 to 125	
<b>Thickener</b>		Lithium Soap	
<b>Base Oil</b>	Type	Polyalphaolefin	
	Kinematic Viscosity	100°C > 30 cSt	ASTM D-445
		40°C > 259 cSt	
	Viscosity Index	155	ASTM D-2270
	Flash Point	°C 250	ASTM D-92
	Pour Point	°C -43	ASTM D-97
Typical Properties of the Grease		Typical Value	Test Method
<b>Color, Appearance</b>		Green, Tacky	
<b>Penetration (1/10 mm)</b>	NLGI Grade	2	ASTM D-217
	Worked	60X 293	
		10k 284	
	Unworked	232	
<b>Density</b>	25°C	0.8581 g/cm <sup>3</sup>	ASTM D-70
<b>Oil Separation</b>	24 hour(s)	100°C 4.6	ASTM D-6184
<b>Evaporation</b>	24 hour(s)	100°C 0.3	NYE CTM

The typical properties shown on this product data sheet should not be used as a basis for preparing specifications. Refer to our product SDS for detailed safety information on this product. (1508)