

A light viscosity, completely fluorinated oil possessing very wide temperature capability, excellent oxidation resistance, excellent plastic and elastomer compatibility and resistance to aggressive chemicals.

Lubricant Properties		Typical Value	Test Method
Recommended Service Range (°C)		-50 to 175	
Color, Appearance		Clear	
Base Oil	Type	Perfluoropolyether	
	Kinematic Viscosity	100°C 40°C	4 cSt 23 cSt
	Viscosity Index		90
	Pour Point	°C	-60
Evaporation	24 hour(s)	100°C	2 %
Density		25°C	1.84

The typical properties shown on this product data sheet should not be used as a basis for preparing specifications. Refer to our product MSDS for detailed safety information because this product. (1402)