

## PFOA Free

A PTFE thickened, light viscosity, completely fluorinated grease possessing very wide temperature capability, excellent plastic and elastomer compatibility and resistance to aggressive chemicals.

Lubricant Properties		Typical Value	Test Method	
<b>Recommended Service Range (°C)</b>		-70 to 200		
<b>Thickener</b>		PTFE		
<b>Base Oil</b>	Type	Perfluoropolyether		
<b>(Uniflor 8710)</b>	Kinematic Viscosity	40°C	26 cSt	ASTM D-445
		-40°C	3000 cSt	ASTM D-445
	Viscosity Index		179	ASTM D-2270
	Flash Point		None, Non-Flammable	ASTM D-92
	Pour Point	°C	-76	ASTM D-97
Typical Properties of the Grease		Typical Value	Test Method	
<b>Color, Appearance</b>		White, Smooth		
<b>Penetration (1/10 mm)</b>	Unworked		276	ASTM D-217
	Worked	60X	288	ASTM D-217
	NLGI Grade		2	ASTM D-217
<b>Density</b>		25°C	1.9 g/cm <sup>3</sup>	NYE CTM
<b>Oil Separation</b>	24 hour(s)	100°C	8	ASTM D-6184
<b>Evaporation</b>	24 hour(s)	100°C	0.7 %	ASTM D-972

The typical properties shown on this product data sheet should not be used as a basis for preparing specifications. Refer to our product SDS for detailed safety information on this product. (1601)