

## **RHEOLUBE 362HF**

广州孚润 400-992-6811

## **PTFE Fortified, Rust Inhibited**

A lithium soap thickened, light viscosity, synthetic hydrocarbon grease for instruments and bearings. Excellent for wide temperature performance.

	Lubricant Properties		Typical Value	Test Method
Recommended Service Range (°C)		-54 to 125		
Thickener			Lithium Soap	
Base Oil	Туре		Polyalphaolefin	
	Kinematic Viscosity	-40°C	8400 cSt	ASTM D-445
		40°C	32.6 cSt	
		100°C	5.7 cSt	
	Viscosity Index		135	ASTM D-2270
	Flash Point	°C	245	ASTM D-92
	Pour Point	°C	-60	ASTM D-97
	Typical Properties of	the	Typical Value	Test Method
	Grease			
Color, Appearance			Off-White, Smooth	
Penetration	NLGI Grade		2	ASTM D-217
(1/10 mm)	Unworked		272	ASTM D-217
	Worked	60X	278	ASTM D-217
Density		25°C	0.92 g/cm <sup>3</sup>	NYE CTM
Oil Separation	24 hour(s)	100°C	2.4	ASTM D-6184
Evaporation	24 hour(s)	100°C	0.1	

The typical properties shown on this product data sheet should not be used as a basis for preparing specifications. Refer to our product SDS for detailed safety information on this product. (1409)