

Rust Inhibited

A PTFE thickened, medium viscosity, completely fluorinated grease intended for bearings and mechanical devices where good film strength is needed at high temperatures and/or fuel or chemical resistance is required

Lubricant Properties		Typical Value	Test Method	
Recommended Service Range (°C)		-30 to 260		
Thickener		PTFE		
Base Oil	Type	Perfluoropolyether		
	Kinematic Viscosity	100°C	33 cSt	ASTM D-445
		40°C	345 cSt	ASTM D-445
	Viscosity Index		134	ASTM D-2270
	Flash Point		None, Non-Flammable	ASTM D-92
	Pour Point	°C	-25	ASTM D-97
Typical Properties of the Grease		Typical Value	Test Method	
Color, Appearance		White, Smooth		
Penetration (1/10 mm)	Unworked		260	ASTM D-217
	Worked	60X	274	ASTM D-217
	NLGI Grade		2	ASTM D-217
Density		25°C	1.94	NYE CTM
Oil Separation	24 hour(s)	150°C	4.3	ASTM D-6184
Evaporation	24 hour(s)	150°C	0.03 %	NYE CTM

The typical properties shown on this product data sheet should not be used as a basis for preparing specifications. Refer to our product MSDS for detailed safety information because this product. (1407)