

A soft, clay thickened, medium viscosity, synthetic hydrocarbon grease intended for electrical devices exposed to arcing conditions.

Lubricant Properties		Typical Value	Test Method
<b>Recommended Service Range (°C)</b>		-20 to 100	
<b>Thickener</b>		Clay	
<b>Base Oil</b>		Polybutene	
	Kinematic Viscosity	100°C 30 cSt	ASTM D-445
		40°C 526 cSt	ASTM D-445
	Viscosity Index	96	ASTM D-2270
	Flash Point	°C 138	ASTM D-92
	Pour Point	°C -35	ASTM D-97
Typical Properties of the Grease		Typical Value	Test Method
<b>Color, Appearance</b>		Light Brown, Smooth	
<b>Penetration</b>	NLGI Grade	1	ASTM D-217
<b>(1/10 mm)</b>	Worked	60X 334	ASTM D-217
	Unworked	334	ASTM D-217
<b>Density</b>		25°C 0.9 g/cm <sup>3</sup>	NYE CTM
<b>Oil Separation</b>	24 hour(s)	100°C 0.8	ASTM D-6184
<b>Evaporation</b>	24 hour(s)	100°C 5 %	ASTM D-972

The typical properties shown on this product data sheet should not be used as a basis for preparing specifications. Refer to our product SDS for detailed safety information on this product. (1408)