



Krytox™ FPG 028

Performance Lubricants

MIL-PRF-27617 G Type IV Grease
Approval No. AFPET/PTPT 12-003

广州孚润 400-992-6811

Product Information

Krytox™ FPG 028 is a smooth, buttery white grease. It has been specifically developed to operate over a wide temperature service range, -73 to 204 °C (-99 to 399 °F), to be resistant to hydrocarbon fuel and liquid oxygen, and to be used as a lubricant in aircraft, aerospace vehicles, and supporting equipment. It is a perfluoropolyether

(PFPE)-based grease thickened with a special high performance PTFE thickener, and has exceptional chemical and oxygen resistance. It is designed to operate under severe conditions, and can be used for bearings, gears, and as a lubricant for O-rings and elastomers.

Properties of Krytox™ FPG 028

CAGE No.: 7GFT8*

Property	Analysis	Specification	Method
Penetration, Unworked	268	225 min.	ASTM D1403
Penetration, Worked	269	235-310	ASTM D1403
Max. Change in Worked Penetration	1	30	ASTM D1403
Corrosion on Copper	1b	2b max.	FTMS 5309
High Temperature Bearing Performance	1691 hr	500 min.	ASTM D3336
Evaporation, % after 22 hr at 204 °C (399 °F)	6.61	15.0 max.	ASTM D2595
Oil Separation, 204 °C (399 °F)	14.25	20% max.	ASTM D6184
Anti-Wear, Scar Diameter mm (max.), 40 kg load			
52100, 75 °C (167 °F)	0.94	1.0 max.	ASTM D2266
52100, 204 °C (399 °F)	0.57	1.3 max.	ASTM D2266
Extreme Pressure Weld, kg (min.)	>800	500 min.	ASTM D2596
Solubility in Fuel	0.1	20% max.	FTMS 5414
Resistance to Fuel	Pass	Pass	FTMS 5414
Resistance to Aqueous Solutions	Pass	Pass	FTMS 5415
Film Stability and Corrosion on Steel	Pass	Pass	PRF 27617, 4.4.4
Liquid Oxygen Impact Sensitivity	0 reactions/20 impacts	No reaction	ASTM D2512
Low Temperature Torque, g-cm at -62 °C (-80 °F) (max.)	Start 533, Run 121	Start 800, Run 300	ASTM D1478
Low Temperature Torque, g-cm at -73 °C (-99 °F) (max.)	Start 1524, Run 364	Start 2800, Run 800	ASTM D1478
Dirt Count			
25-74 Micron	45/cc	1000 max.	FTMS 3005
Over 75 Micron Diameter	0	0	FTMS 3005
Additional Data			
Pour Point	<-69 °C (-92 °F)	—	ASTM D97
Water Washout, % at 38 °C (100 °F)	0.32	—	ASTM D1264
Oil Viscosity at 40 °C (104 °F), cSt	50.45	—	ASTM D445

*Code for Mil-Spec

Storage and Handling

Does not oxidize or degrade from atmospheric contact. Life of uncontaminated product in reclosed container is undiminished. Indefinite shelf life in unopened container.

It is normal for oil to separate from grease during storage. Before use, knead tubes or stir larger containers to remix.

Product Package

Krytox™ FPG 028 is available in 50 and 100 g syringes, 8 oz tubes, and 1.76 lb cartridges.



The information set forth herein is furnished free of charge and based on technical data that Chemours believes to be reliable. It is intended for use by persons having technical skill, at their own discretion and risk. The handling precaution information contained herein is given with the understanding that those using it will satisfy themselves that their particular conditions of use present no health or safety hazards. Because conditions of product use are outside our control, Chemours makes no warranties, express or implied, and assumes no liability in connection with any use of this information. As with any material, evaluation of any compound under end-use conditions prior to specification is essential. Nothing herein is to be taken as a license to operate under or a recommendation to infringe any patents.

NO PART OF THIS MATERIAL MAY BE REPRODUCED, STORED IN A RETRIEVAL SYSTEM OR TRANSMITTED IN ANY FORM OR BY ANY MEANS ELECTRONIC, MECHANICAL, PHOTOCOPYING, RECORDING OR OTHERWISE WITHOUT THE PRIOR WRITTEN PERMISSION OF CHEMOURS.

For product information, industry applications, technical assistance, or global distributor contacts, visit krytox.com or within the U.S. and Canada, call 1-844-773-CHEM/2436 or outside of the U.S., call 1-302-773-1000.

© 2016 The Chemours Company FC, LLC. Krytox™ and any associated logos are trademarks or copyrights of The Chemours Company FC, LLC. Chemours™ and the Chemours Logo are trademarks of The Chemours Company.

C-10684 (6/16)